



## APPLICATION BULLETIN

### A Spray Applied Architectural Membrane Using Poly BD® Liquid Resins

The following is a starting point formulation for a Poly BD® resin asphalt based architectural membrane. It is designed to be spray applied. An airless two component mix meter piece of equipment such as Binks Formulator G can be used.

This formulation exhibits good mechanical properties. It also has a low MVTR as well as excellent resistance to 20% NaOH and 20% H<sub>2</sub>SO<sub>4</sub>. To obtain resistance to 20% HC1, 2-ethyl-1, 3-hexanediol should be substituted for Voranol 220-530 diol on the same hydroxyl basis, 1:1. The overall properties of this membrane make this an excellent starting point formulation for between slab, below grade, or buried waterproofing applications. Above ground applications can be considered if the membrane is properly protected from direct sunlight.

#### Starting Point Formulation

	<u>Component</u>	<u>Parts by Weight</u>
Part A	Poly BD® R45 HTLO Resin	100.0
	Voranol 220-530 <sup>6</sup> Asphalt	8.6
	AC20 <sup>1</sup>	72.9
	Circosol 430 Oil <sup>2</sup>	72.9
	Cyanox® 2246 <sup>3</sup>	1.0
	Sterling® R (Carbon Black) <sup>4</sup>	2.0
	T-12 Catalyst <sup>5</sup>	3-4 drops
Part B	Isonate® 143L <sup>6</sup>	25.5
	NCO/OH = 1.05	
	Mix Ratio Volume – 13/1	
	Mixed Viscosity = 6200 cps at 25°C	
	MVTR (metric perms) = 0.168	
Mechanical Properties:		
	Tensile (psi)	370
	Elongation (%)	419
	Modulus 100% (psi)	100
	200% (psi)	160
	300% (psi)	240
	Tear Die C (pli)	49
	Hardness (Shore A)	36

#### Chemical Resistance<sup>1</sup>

	<u>Initial</u>	<u>20% NaOH</u>	<u>20% H<sub>2</sub>SO<sub>4</sub></u>
Tensile strength (psi)	370	377	315
Elongation (%)	419	433	335
Modulus 100% (psi)	100	104	104
200% (psi)	160	172	177
300% (psi)	240	255	274
Tear Die C (pli)	49	48	55
Hardness (Shore A)	36	38	40

<sup>1</sup>Samples were immersed in test media for one week at 160°F.

#### Suppliers List

<sup>1</sup>Exxon, Koch

<sup>2</sup>Sun Oil Co (Belgium), Naphthenic oils

<sup>3</sup>Cytec Industries, Inc

<sup>4</sup>Cabot Corp

<sup>5</sup>Air Products & Chemicals

<sup>6</sup>Dow Chemical - ISONATE pure and modified MDI products are potentially hazardous materials and require care in handling.



## About Resin Solutions

Resin Solutions is the premier global supplier of specialty chemical additives, hydrocarbon specialty chemical, and liquid and powder tackifying resins used as ingredients in adhesives, rubbers, polymers, coatings and other materials. Resin Solutions has pioneered the development of these advanced technologies, introducing products that enhance the performance of products in energy, printing, packaging, construction, tire manufacture, electronics, and other demanding applications.

For more information, please visit [www.resinsolutions.com](http://www.resinsolutions.com).

## Resin Solutions

665 Stockton Drive, Suite 100  
Exton, PA 19341  
1-484-284-8998

\*The information in this bulletin is believed to be accurate, but all recommendations are made without warranty since the conditions of use are beyond Resin Solutions control. The listed properties are illustrative only, and not product specifications. Resin Solutions disclaims any liability in connection with the use of the information, and does not warrant against infringement by reason of the use of its products in combination with other material or in any process.